



DL Labs, Inc.  
74 Kent Street  
Brooklyn, New York 11222-1517

Phone (718) 383-5080  
Fax (718) 383-7445  
E-mail: [info@dllabs.com](mailto:info@dllabs.com)  
[dllabs@aol.com](mailto:dllabs@aol.com)

---

Accredited by National Voluntary Laboratory Accreditation Program - Lab Code 100252  
Accepted by Canadian General Standards Board - No. 76005 - ISO/IEC 25 Approved

August 16, 2005

Fine Paints of Europe  
P. O. Box 419  
Route 4 West  
Woodstock, VT 05091-0419

Att: Mr. John F. Lahey Jr.

Re: DL-14593R  
Via FAX 802-457-3984

### OBJECTIVE

To evaluate the adhesion and bleed through resistance of ***Oil Primer / Undercoat*** when applied to mahogany.

### PRODUCT TESTED

The primer was submitted by Fine Paints of Europe for evaluation. The primer was identified as:

**Fine Paints of Europe, *Oil Primer / Undercoat*,**  
High Performance Primer / Undercoat for Interior and Exterior Use,  
White Lot: 04381129

### PROCEDURES

One coat of ***Oil Primer / Undercoat*** was applied to solid Honduran mahogany at 70-80µm (3-mils) wet film thickness and allowed to dry 24-hours at standard conditions before testing.

The following test procedures were conducted in this evaluation:

***Adhesion***, ASTM Test Method D 3359, Method A - Cross-cut "X" Tape Test

***Stain Resistance - Bleed Through*** - The coated mahogany test substrate was subjected to heat with humidity for 24 and 96-hours. The stain resistance or bleed through was determined as the difference in directional reflectance. A reflectance difference no greater than 20% has been deemed acceptable as stated in federal government specifications (TT-P-001984, sec. 3.3.7).



## **TEST RESULTS**

The test results can be found in the Appendix.

An ASTM D 3359 Adhesion test rating of 5A denotes that “No peeling or removal of film along incisions” was observed.

## **CONCLUSIONS**

The following conclusions may be derived from this evaluation:

1. The ***Oil Primer / Undercoat*** product exhibited excellent adhesion to mahogany both before and after exposure to humidity.
2. The ***Oil Primer / Undercoat*** product did not exhibit bleed through when applied to mahogany and exposed to hot/humid conditions for 24 and 96 hours.

**DL Labs, Inc.**

Mario Lazaro, Jr.  
Assistant Technical Director

cc: T. Sliva



APPENDIX

TEST RESULTS

OIL PRIMER / UNDERCOAT

	<u>Result</u>
<b>Adhesion of Primer to Honduran Mahogany</b>	
Initial	5A
After 24 hours exposure to humidity	5A
After 96 hours exposure to humidity	5A
<b>Stain Resistance - Bleed Through</b>	
Visible Color Change	
After 24-hours exposure	None
After 96-hours exposure	None
Reflectance Change	
Before exposure	83.6%
After 24-hours exposure	83.3%
Difference	0.3%
After 96-hours exposure	83.5%
Difference	0.1%