

MARSHALL LABORATORIES, INC.

2060 Palmetto St. • Clearwater, FL 33765 • Phone (727) 443-2771 • FAX (727) 443-2777

Results

	Improved Hollandlac Billiant Base White	
Gloss - ASTM D523		
Gloss, 20 Degrees	82.3	
Gloss, 60 Degrees	90.1	
Gloss, 85 Degrees	98.7	
Yellowing Resistance		
Initial CIELAB Values		
L*	96.99	
a*	-1.32	
b*	2.66	
Chart Exposed to Ammonia (30 Minutes) (1)		
L*	96.69	
DL*	-0.30	
a*	-1.84	
Da*	-0.52	
b*	4.77	
Db*	2.11	Db* = 0 = No yellowing
DE		
Leveling		
Leneta, ASTM D4062	10	10 = Perfect flow & leveling rating



Daniel Marschall
Marschall Labs Inc.
July 11, 2017